

Collection Leading

Genuine leather

Technical data sheet leather Leading

<u>GENERAL</u>		
Thickness		1.2-1.4
Average surface		4,5 sqm
Finishing		aniline, chrome tanned
<u>TESTS</u>	<u>METHOD</u>	<u>RESULT / U.M.</u>
Fastness to rubbing - dry	UNI EN ISO 11640	>3 grey scale / dry: 500
Fastness to rubbing - wet	UNI EN ISO 11640	>3 grey scale / wet: 80
Fastness to rubbing - perspiration	UNI EN ISO 11640	>3 grey scale / alkaline: 50
Adhesion of finish	UNI EN ISO 11644	>2 N/mm
Fastness to light Xenon	UNI EN ISO 105 B 02	>3 – blue scale
Flexing endurance Ballyflex	UNI EN ISO 5402	50.000 cycles
Tensile strength	UNI EN ISO 3376	>10 N/mm ²
Tear strength	UNI EN ISO 3377-2	>20N
Elongation at break	UNI EN ISO 3376	40-70%
<u>CERTIFICATS</u>		
<u>CLEANING INSTRUCTIONS</u>		
<u>REMARKS</u>		
***INTENSIVE DOMESTIC USE		
Slight color differences between production batches can occur.		
The test results only apply to the samples tested.		
Buvetex can't be kept liable for inappropriate use of the genuine leather.		