

Collection Varzeze

Genuine leather

Technical data sheet

<u>GENERAL</u>		
Thickness		0,8-1,0 mm
Average surface		4,8-5,0 sqm
Finishing		half grain S.A. bovine
<u>TESTS</u>	<u>METHOD</u>	<u>RESULT / U.M.</u>
Fastness to rubbing Veslic- dry	UNI EN ISO 11640	>= 4
Fastness to rubbing Veslic- wet	UNI EN ISO 11640	>= 3/4
Rub fastness Crock test (dry / wet)	UNI EN ISO 105 X 12	-
Colour fastness to light	UNI EN ISO 105 B 02	>= 5
Sweat fastness (alkaline solution)	UNI EN ISO 11640	>= 3/4
Flexing endurance Bally Flex	UNI EN ISO 5402	>50.000 cycles
Tensile strength	UNI EN ISO 3376	-
Elongation at break	UNI EN ISO 3376	-
Tear strength (Bauman Method)	UNI EN 3377-1	>= 20
Finish adhesion	UNI EN ISO 11644	>= 2,5
Burning behaviour	-	-
<u>CERTIFICATS</u>		
<u>CLEANING INSTRUCTIONS</u>		
<u>REMARKS</u>		
**** INTENSIVE DOMESTIC/CONTRACT USE		
Slight color differences between production batches can occur.		
The test results only apply to the samples tested.		
Buvetex can't be kept liable for inappropriate use of the artificial leather.		